

MATERIAL PROPERTY DATA SHEET



EXCEL PP5-10™


Equivalent and Replaces: P300LW • ETPP-10
Permanent • Double Net • Poly-Fiber Matrix •
Turf Reinforcement Mat

DESCRIPTION

Excel PP5-10 Turf Reinforcement Mat (TRM) is composed of 100% synthetic green fibers mechanically (stitch) bound between two UV stabilized, synthetic nets. Stitching is secured on two-inch centers using UV stabilized, synthetic thread. Excel PP5-10 is a permanent, three-dimensional TRM that provides immediate erosion protection and long-term turf reinforcement and is intended for applications requiring erosion protection for greater than thirty-six months.

Each roll of Excel PP5-10 is made in the USA and manufactured under MKB Company's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.

PP5-10 is compliant and/or exempt with the Build America, Buy America Act, §§ 70901–70927 of the Investment and Jobs Act (Pub L. 117-58), 2 CFR Part 184 – Buy America Preferences for Infrastructure Projects and OMB Memorandum M-22-11.



Material Content	
Matrix	Synthetic Fibers

Netting	Top Net: Mediumweight, UV stable
	Bottom Net: Mediumweight, UV stable

Thread	Synthetic, UV Stable
--------	----------------------

Standard Roll Sizes				
Width	8 ft	(2.4 m)	16 ft	(4.9 m)
Length	112 ft	(34.0 m)	112 ft	(34.0 m)
Weight ± 10%	63 lb	(29.0 kg)	126 lb	(58.0 kg)
Area	100 sy	(83.6 m ²)	200 SY	(167.0 m ²)
Part Number	PP5 10-8X112.5		PP5 10-16X112.5	

Material available in custom roll sizes

Approvals & Classification	
Classification	FHWA: Type 5.C / ECTC: 5.D
TTI Approvals	Class 2 Type H
NTPEP Number	ECP-2018-04-009

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by MKB Company or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact MKB Company

©2026, MKB Company is a registered trademark from MKB. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.

Index Property	Test Method	Typical	
Thickness	ASTM D6525	0.38 in.	(10 mm)
Mass/Unit Area	ASTM D6566	10.0 oz/sy	(350 g/sm)
Tensile Strength – MD	ASTM D6818	325 lbs/ft	(4.7 kN/m)
Tensile Strength – TD	ASTM D6818	225lbs/ft	(3.3 kN/m)
Elongation - MD	ASTM D6818	25%	
Elongation – TD	ASTM D6818	30%	
UV Stability	ASTM D4355	80% @1000 hr	
Light Penetration	ASTM D6567	25%	
Biomass Improvement	ASTM D7322	400%	
Specific Gravity	ASTM D792	57.4 lb/ft ³	(0.92 g/cm ³)
Porosity	ECTC	96%	

Design Parameters		
Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.03	N/A
Slope Maximum Gradient ¹	0.5H:1V	0.5H:1V
Permissible Shear Stress ²	2.3 psf (110 Pa)	12.0 psf (575 Pa)
Permissible Velocity ²	8.0 fps (2.4 m/s)	18.0 fps (5.5 m/s)
τ_{veg} / τ_{TRM} (HEC-15)	N/A	0.55

Manning's n Roughness (HEC-15)		
τ_{lower}	τ_{mid}	τ_{upper}
0.035	0.028	0.027

1 Maximum Gradient a recommendation for typical insllations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation



mkbcompany.com | 888-578-0777