

MATERIAL PROPERTY DATA SHEET




VMax[®] S200[™]

Permanent • Triple Net • Organic Fiber Matrix •
Turf Reinforcement Mat

DESCRIPTION

S200 Turf Reinforcement Mat (TRM) is composed of 100% straw fibers mechanically (stitch) bound between a three-dimensional UV stabilized, synthetic net structure. Stitching is secured on two-inch centers using UV stabilized, synthetic thread. S200 is a permanent, three-dimensional TRM that provides immediate erosion protection and long-term turf reinforcement and is intended for applications requiring erosion protection for greater than thirty-six months.

Each roll of S200 is made in the USA and manufactured under North American Green's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.



Material Content	
Matrix	Straw
Netting	Top Net: Medium-weight, UV stable
	Middle Net: Corrugated Heavyweight, UV stable
	Bottom Net: Medium-weight, UV stable
Thread	Synthetic, UV Stable

Standard Roll Sizes		
Width	8 ft	(2.4 m)
Length	90 ft	(27.4 m)
Weight ± 10%	64 lb	(29.0 kg)
Area	80 sy	(66.9 m ²)
Part Number	S200-8X90	

Material available in custom roll sizes

Approvals & Classification	
Classification	FHWA: Type 5.C / ECTC: Type 5.C
TTI Approvals	Class 2 Type H
NTPEP Number	ECP-2022-01-010

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by MKB Company or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact MKB Company

©2026, North American Green is a registered trademark from MKB. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.

Index Property	Test Method	Typical	
Thickness	ASTM D6525	0.50 in.	(13 mm)
Mass/Unit Area	ASTM D6566	12.0 oz/sy	(400 g/sm)
Tensile Strength – MD	ASTM D6818	450 lbs/ft	(6.6 kN/m)
Tensile Strength – TD	ASTM D6818	450 lbs/ft	(6.6 kN/m)
Elongation - MD	ASTM D6818	30%	
Elongation – TD	ASTM D6818	20%	
UV Stability	ASTM D4355	80% @1000 hr	
Light Penetration	ASTM D6567	15%	
Biomass Improvement	ASTM D7322	300%	
Specific Gravity	ASTM D792	57.4 lb/ft ³	(0.92 g/cm ³)
Porosity	ECTC	N/A	

Design Parameters		
Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.05	N/A
Slope Maximum Gradient ¹	0.5H:1V	0.5H:1V
Permissible Shear Stress ²	2.3 psf (110 Pa)	10.0 psf (480 Pa)
Permissible Velocity ²	8.5 fps (2.6 m/s)	15 fps (4.6 m/s)
τ_{veg} / τ_{TRM} (HEC-15)	N/A	0.67

Manning's n Roughness (HEC-15)		
τ_{lower}	τ_{mid}	τ_{upper}
0.038	0.030	0.026

1 Maximum Gradient a recommendation for typical insllations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation

